

















**OKITE®**

[www.okite.com](http://www.okite.com)

A large, light grey spiral graphic that starts from the center and expands outwards, filling the lower two-thirds of the page. It is composed of several concentric, slightly offset spiral lines.

**OKITE®**  
Technical Data

## OKITE® Technical Data

	<b>Characteristics</b>	<b>Unit of Measurement</b>	<b>Average Value (Fine Structure)</b>	<b>Average Value (Large Structure)</b>	<b>Sample</b>	<b>Standards Employed</b>
	Density	Kg/mc	2110,0	2110,0	5 x 5 x 2 cm	EN 14617-1
	Water Absorbion	C media %	0.07	0.07	5 x 5 x 2 cm	EN 14617-1
	Bending Strength	Mpa	65,7	51,7	5 x 20 x 2 cm	EN 14617-2
	Compression Strength	N/mmq	159		7 x 7 cm <sup>3</sup>	EN 14617-15
	Deep Abrasive Strength	mm	Max 29.5 - Min 28.5	Max 27.5 - Min 26.5	15 x 15 x 2 cm	EN 14617-4
	Thermal conductivity	W/(m*K)	2,0 <sup>±0.3</sup>	3,1 <sup>±0.6</sup>	50 x 50 x 3 cm	EN 12664
	Dimensional Stability	Δ	0,05 (Class A)	0,08 (Class A)	30 x 30 x 2 cm	EN 14617-12
	Impact Strength	Joule	11,4	4,9	20 x 20 x 2 cm	EN 14617-9
	Fire Resistance	Class	B	B		UNI EN 13501-1
	Frost Resistance	KMf25	107,2	102,7	20 x 5 x 2 cm	EN 14617-5
	Chemical Resistance	Classe	C4	C4	20 x 20 x 2 cm	UNI EN 14617-10
	Thermal Shock Resistance	ARf 20%	-4,1	-0,58	20x 5 x 1 cm	UNI EN 14617-6
	Colour Resistance to Light	Variation of Colour	Slight			
	Lead and Cadmium releas	mg/dm <sup>2</sup>	0		30 x 30 x 1 cm	UNI EN ISO 10545-15

\*Values stated



**OKITE®**

[www.okite.com](http://www.okite.com)

## EUROPE

### **SIC s.r.l.**

Corso Vittorio Emanuele II,30  
20122 MILANO (MI)  
Italia

Tel.: +39 02 870 72 836

Fax: +39 02 870 72 837

---

## USA

### **Seieffe Corporation**

Importer & Master Distributor  
12227 K FM 529  
Northwoods Industrial Park  
Houston - Tx 77041  
United States

Tel.: +1 713 849 3800

Fax: +1 713 849 3835

Toll Free:+1 866 654 8397

---

## UNITED KINGDOM

### **Seieffe UK Ltd**

104 High Street London  
Colney AL2 1QL  
Tel. 01992 470 801  
Fax. 01992 470 799

---

[okite@okite.com](mailto:okite@okite.com)  
[www.okite.com](http://www.okite.com)